



## **TEKNOFILLER LIGHT**

## Catalog No: 1200 - 153

Teknofiller Light Filler is a two-pack, solventless epoxy filler, with low specific weight. It provides excellent results with primers that are applied on steel, wooden, glass-fiber reinforced polyester and aluminum surfaces. It is especially preferred for speed boats due to its lightness. Fillings up to 1 - 2 cm can easily be performed. This product does not hollow on the surface on which it is applied. Its sanding is excellent.

## TECHNICAL CHARACTERISTICS

Solids by volume (%)	: 100
Density (mixture) (gr/cm <sup>3</sup> )	: 0,70 ~ 0,75
Color	: Component A = white, Component B = brown
Finish	: Matt
Binder	: Epoxy resin
Heat resistance (ºC)	: 150
Application temperature (°C)	: + 5 ~ + 35
Drying time (25 °C)	
beginning of drying (hrs)	: 1~2
ready for sanding (hrs)	: 12
Relative humidity (%)	: 85
Thinner	: Not suitable.
Application mode	: Steel spatula, trowel
Surface preparation	: The filler or epoxy primer existing on the surface must be cleaned, degreased and sanded with 60 grade paper. The surface must be sanded before

Mixing ratio (by weight and by volume) Pot life of the mixture (hrs)(20 °C) Safety precautions : 1A/1B

applying the next coat.

: Max. 1

: Irritating to eyes and skin. May cause sensitisation by skin contact. Toxic to aquatic organisms, may cause long-term adverse effects in the aquatic environment. Keep out of the reach of children. Avoid contact with skin and eyes. Do not empty into drains, dispose of this material and its container at hazardous or special waste collection point. Wear suitable gloves and eye/face protection. If swallowed, seek medical advice immediately and show this container or label. Wear suitable gloves. Dispose of this material and its container to hazardous or special waste collection point.

FP.01.03.Rev 00



Tuzla Deri Org. Sanayi Bölgesi 7.Yol D-12 Parsel Tuzla • İstanbul Tel: 0 216 394 16 50 (pbx) • Faks: 0216 394 16 99 • info@teknomarin.com.tr www.teknomarin.com.tr