

TEKNOFILLER REPAIR

Catalog No: 1200 - 150

Teknofiller Repair is a general purpose two-pack epoxy filler. It is applied on Teknofiller Dolgu (1200-152) and Teknofiller Light (1200-153) fillers which are on steel, wooden, glass-fiber reinforced polyester and aluminum surfaces. It is used for preparing a base to the final coat primer or Teknofiller Spray (1200-151) and Teknopox Epoxy HI-Build (1000-103HB) spray fillers. This product does not absorb the final coat primer. It is applied easily and its sanding is good.

TECHNICAL CHARACTERISTICS

Solids by volume (%)	:	100
Density (mixture) (gr/cm³)	:	1.5
Color	:	Component A = white, Component B = gray
Finish	:	Matt
Binder	:	Epoxy resin
Heat resistance (°C)	:	120
Application temperature (°C)	:	+ 5 ~ + 35
Drying time (25 °C)		
beginning of drying (hrs)	:	3 ~ 5
ready for sanding (hrs)	:	24
Relative humidity (%)	:	85
Thinner	:	Not suitable.
Application mode	:	Steel spatula, trowel.
Surface preparation	:	The surface must be sanded and free from oil, grease, dirt and moisture. The surface must be sanded before applying the next coat.
Mixing ratio (by weight)	:	1 A / 1 B
Pot life of the mixture (hrs) (20 °C)	:	2 ~ 4
Safety precautions	:	Irritating to eyes and skin. May cause sensitisation by skin contact. Toxic to aquatic organisms, may cause long-term adverse effects in the aquatic environment. Keep out of the reach of children. Avoid contact with skin and eyes. Do not empty into drains, dispose of this material and its container at hazardous or special waste collection point. Wear suitable gloves and eye/face protection. If swallowed, seek medical advice immediately and show this container or label.