



TEKNOFILLER SPRAY

Catalog No: 1200 - 151

Teknofiller Spray is a spray type, two-pack epoxy filler. It is applied on Teknofiller Dolgu (1200-152), Teknofiller Light (1200-153) and Teknofiller Repair (1200-150) fillers which are on steel, wooden, glass-fiber reinforced polyester and aluminum surfaces. It covers well the sanding marks and minimizes the surface faults as well as prepares an excellent ground for the final coat primer. Application with pressurized air gun and airless spray is preferred.

TECHNICAL CHARACTERISTICS

Solids by volume (%) Density (mixture) (gr/cm ³) Color Finish Binder Heat resistance (°C) Application temperature (°C) Drying time (25 °C)	 70 1,15 ~ 1,25 Component A = rose, Component B = khaki Matt Epoxy resin 150 + 5 ~ + 35
beginning of drying (hrs) ready for sanding (hrs) Relative humidity (%) Thinner Application mode Surface preparation	 : 3 ~ 5 : 24 : 85 : 3 - 10 % Teknomarin Epoxy Boya Tineri (1001) : Spray gun, airless spray gun. : The surface must be sanded and free from oil, grease, dirt and moisture. The surface must be sanded before applying the second coat.
Mixing ratio (by weight) Pot life of the mixture (hrs)(20 °C) Safety precautions	 1 A / 1 B 4 ~ 6 Flammable. Harmful by inhalation and in contact with skin. Irritating to eyes and skin. May cause sensitisation by skin contact. Toxic to aquatic organisms, may cause long-term adverse effects in the aquatic environment. Keep out of the reach of children. Do not breathe gas/ fumes/ vapour/ spray (appropriate wording to be specified by the manufacturer). Avoid contact with skin and eyes. Do not empty into drains, dispose of this material and its container at hazardous or special waste collection point. Wear suitable gloves and eye/face protection. If swallowed, seek medical advice immediately and show this container or label. Use only in well-ventilated areas. Wear suitable protective clothing and gloves.

FP.01.03.Rev 00



Tuzla Deri Org. Sanayi Bölgesi 7.Yol D-12 Parsel Tuzla • İstanbul Tel: 0 216 394 16 50 (pbx) • Faks: 0216 394 16 99 • info@teknomarin.com.tr www.teknomarin.com.tr