

TEKNOGLOSS LUX SENTETİK

Catalog No: 6000 - 111

This product is a resistant paint used on steel, iron and wooden surfaces. Its gloss is perfect. This product is applied on primers such as Teknomarin Yat Sülyen (6000-101A), Teknomarin Synthetic Anti-Rust Primer (6000-102) and Teknomarin Sentetik Arakat (6000-103).

TECHNICAL CHARACTERISTICS

Solids by volume (%)	: 55 (according to the color)
Density (gr/cm³)	: 1,15 ~ 1,20
Color	: Requested colors
Finish	: Glossy
Binder	: Alkyd resin
Dry film thickness (μ)	: 35
Theoretical covering capacity (m²/lt)	: 15 (35μ) - 11 (50μ)
Application temperature (°C)	: + 5 ~ + 35
Drying time (25 °C)	
beginning of drying (hrs)	: 2
full drying (hrs)	: 4
Thinner	: 5% for brush, 10-15% for spray application; by Teknomarin Sentetik Boya Tineri (6001).
Application mode	: Brush, roller, spray gun.
Spray Equipment (Conventional)	
Nozzle size	: 1,2 – 1,4 mm
Nozzle pressure	: 3-3,5 atm
(Airless)	
Nozzle size	: 0,013 – 0,021 inch
Nozzle pressure	: 12 – 15 mpa
Surface preparation	: The surface must be free from dirt, oil, grease and moisture.
Safety precautions	: May cause cancer. May cause heritable genetic damage. Flammable. Avoid exposure - obtain special instructions before use. Keep locked up and out of the reach of children. Do not breathe gas/ fumes/ vapour/ spray (appropriate wording to be specified by the manufacturer). Do not empty into drains, dispose of this material and its container at hazardous or special waste collection point. In case of insufficient ventilation, wear suitable respiratory equipment. In case of accident or if you feel unwell, seek medical advice immediately (show the label where possible).